

09-19-00

A

## IN THE U.S. PATENT AND TRADEMARK OFFICE

Express Mail Label No.: EK 588 818 192 US

Attorney Docket No.: HOG422

Applicant(s): Andreas HAJEK, Thomas HECK, Stefan HARKE,  
and Thomas WILHELM

Title: Moulding Compositions For The Production Of  
Sanitary-ware Components

Box Patent Application  
The Commissioner of Patents and Trademarks  
Washington, D.C. 20231

Sir:

This is a request for filing a continuation application under 37 CFR 1.53 and 35 USC 111(a) of pending prior international PCT application:  
PCT Application No.: PCT/EP99/01121 Filed: February 20, 1999

Applicant(s): Andreas HAJEK, Thomas HECK, Stefan HARKE,  
and Thomas WILHELM

For: Moulding Compositions For The Production Of  
Sanitary-ware Components

- [X] Enclosed is an English translation of the prior German language PCT application No. PCT/EP99/01121 and an affidavit or declaration by the translator verifying it as a true and correct translation.
- [ ] A Declaration and Power of Attorney executed by the inventors is enclosed.
- [X] The filing fee is calculated as follows after entering the enclosed Preliminary Amendment:

For	No. Filed	No. Extra	(X) LG Entity	RATE	( ) SM Entity	Fee
Basic Fee				\$690.00	\$345.00	\$690.00
Total Claims ( 16 - 20 = 0)			x	\$ 18.00	x \$ 9.00	0.00
Indep. Claims ( 1 - 3 = 0)			x	\$ 78.00	x \$ 39.00	0.00
[0] Multiple Dependent Claim			+	\$260.00	+ \$130.00	0.00
* * * TOTAL FILING FEE * * *						\$ 690.00

5. [X] A check for \$690.00 is enclosed to cover fees.
6. [X] The Commissioner is hereby authorized to charge any additional filing fees under 37 CFR 1.16 which may be required by this communication to Deposit Account No. 20-1124. A duplicate copy of this sheet is enclosed.



09-19-00, 09-18-00, 09-18-00

7. ☐ A Verified Statement under 37 CFR 1.9 and 1.27 regarding small entity status:
- a. ☐ was filed in prior application Serial No. \_\_\_\_\_ filed \_\_\_\_.
- b. ☐ is enclosed. (Not required if a Verified Statement is in the prior application.)
8. ☐ Cancel in this application original Claim \_\_\_\_ of the prior application before calculating the filing fee. (Retain at least one independent claim.)
9. ☒ Amend the specification by inserting before the first line the sentence: ---This is a continuation of international PCT application No. PCT/EP99/01121 having international filing date of February 20, 1999, which designates the United States.---
10. ☐ Transfer the formal drawings from the prior application to this application and abandon said prior application as of the filing date accorded this application. A duplicate copy of this sheet is enclosed for filing in the prior application file. (May only be used if signed by a person authorized by 37 CFR 1.138 and before payment of the issue fee.)
11. ☐ \_\_\_\_\_ Drawing sheets enclosed:
- ☐ bristol board
- ☐ soft copy
12. ☒ Priority is claimed under 35 USC 365(c) and 120 based on international PCT Application No. PCT/EP99/01121 filed February 20, 1999, which designates the United States and German Application Serial No. 198 12 122.9, filed March 19, 1998.
13. ☐ Assignment Recordation Cover Sheet and Assignment.
14. ☒ A Preliminary Amendment is enclosed. Please enter before calculating the filing fee.
15. ☐ An Amendment Before First Office Action is enclosed. (Claims added are numbered consecutively beginning with the number next following the highest numbered original claim.)
16. ☐ I hereby verify that the attached papers are a true copy of prior application Serial No. \_\_\_\_ as originally filed on \_\_\_\_\_.
17. ☒ Acknowledgment Postal Card
18. ☐ Information Disclosure Statement

19. [X] Pursuant to 37 CFR 1.53, this application is being filed without the declaration or oath. Please notify the undersigned of the due date for submitting the declaration or oath. A Power of Attorney in favor of the undersigned will be submitted later. Please direct all correspondence to the address set forth below.

The inventors are Andreas HAJEK, Thomas HECK, Stefan HARKE, and Thomas WILHELM, all German.

The undersigned declares further that all statements made herein of his own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

Please address all telephone calls to the undersigned at (616) 353-8807. Please address all correspondence to:

Edward J. Timmer  
Walnut Woods Centre  
5955 W. Main Street  
Kalamazoo, Michigan 49009

The undersigned is: [ ] an attorney of record in the prior application.

[X] acting under 37 CFR 1.34(a).

IN DUPLICATE

Respectfully submitted,



EJT/gg

Edward J. Timmer (Reg. No. 27 402)

Walnut Woods Center  
5955 W. Main Street  
Kalamazoo, Michigan 49009

Tel: (616) 353-8807  
Fax: (616) 372-3217

Encl: Listed Above

PATENT APPLICATION

Express Mail Label No.: EK 588 818 192 US

IN THE U.S. PATENT AND TRADEMARK OFFICE

September 12, 2000

Applicant(s): Andreas HAJEK et al.

For : Moulding Compositions For The Production Of  
Sanitary-ware Components

Atty. Docket  
No.: HOG422

The Commissioner of Patents and Trademarks  
Washington, D. C. 20231

PRELIMINARY AMENDMENT

Sir:

Prior to calculation of the filing fee in the above-identified application, kindly enter the following:

IN THE CLAIMS

Please amend the following claims as follows:

Claim 3, line 1; delete "or 2".

Claim 4, lines 1 and 2; replace "one of Claims 1 to 3"  
with -- Claim 1 --.

Claim 5, lines 1 and 2; replace "one of the preceding claims"  
with -- Claim 1 --.

Claim 7, line 1; delete "or 6".

Claim 8, line 1; delete "or 6".

Claim 9, lines 1 and 2; replace "one of Claims 5 to 8"  
with --- Claim 5 ---.

Claim 10, lines 1 and 2; replace "one of Claims 5 to 9"  
with --- Claim 5 ---.

Claim 11, lines 1 and 2; replace "one of the preceding claims"  
with --- Claim 1 ---.

00344 0300  
00344 0300

Claim 14, lines 1 and 2; replace "one of Claims 1 to 13"  
with --- Claim 1 ---.

The foregoing amendments effect claim cancellation through the elimination of multiple dependency in order to reduce the filing fee. Entry of this amendment prior to calculation of the filing fee is respectfully requested.

Edward J. Tamm

Encl: None

I, Eur Ing James Francis Bradley BSc CEng MIEE MIL,  
translator to Engineering Translations, of "Hollyhocks",  
Cherry Tree Road, Farnham Royal, Buckinghamshire,  
England, hereby declare that I am conversant with the  
German and English languages and am a competent  
translator thereof. I declare further that to the best  
of my knowledge and belief the following is a true and  
correct translation of the accompanying documents in the  
German language.

Signed this 18<sup>th</sup> day of August 2000

A handwritten signature in black ink, appearing to be 'JFB' with a long, sweeping horizontal stroke extending to the right.

J. F. BRADLEY

For and on behalf of Engineering Translations

003750 "T424960

**Moulding Compositions for the Production of Sanitary-  
ware components**

The invention relates to a moulding composition for the production of sanitary-ware components, which comprises a methyl-methacrylate-based syrup and from 50 to 85%, expressed in terms of the moulding composition, of an inorganic filler. The invention furthermore concerns sanitary-ware components produced from such moulding compositions, the term sanitary-ware components being used in the wide sense and besides wash-basins, shower bases, bathtubs, also covering kitchen sinks, work surfaces and the like.

Many moulding compositions of the type described in the introduction are known from the literature, for example from German Patent DE 2449656 and European patent application EP 0361101 or WO 95/23825.

Because of the not very high impact strength of the cured moulding-composition materials, the shaped components need to be designed with a relatively large wall thickness (sometimes in excess of 10 mm). Wall thicknesses of this order lead, especially in the case of formulations in which intentional sinking of coarse filler particles towards the visible side takes place, to very uneven reverse sides and, in the case of kitchen sinks, the drainage holes often exhibit high degrees of roughness or even bubbles. This causes problems in the subsequent processing. In particular, this can give rise to leaks in the outlet fixture, especially if a moulding-composition burr needs to be ground down.

In the case of moulding compositions which are produced using cristobalite powders, i.e. a very fine-grained material, as filler, relatively poor scratch-proofness and abrasion resistance are found, whereas the aforementioned moulding compositions with rela-

095424.091300

tively coarse, sinking fillers have a relatively high degree of surface roughness.

In general, the syrup production necessarily requires the addition of pre-polymeric methacrylate, hereafter abbreviated to PMMA, which demands longer solution times for the PMMA in the methyl methacrylate monomers. This increases the production times, and hence the production costs as well.

The moulding compositions finally obtained, with the necessary viscosities, entail relatively long filling times for the moulds, which may sometimes exceed one minute in the case of moulds which are used for the production of kitchen sinks, even if filling pressures of 5 bar are used.

The object of the present invention is to provide a moulding composition which, especially when cristobalite powders are used as the filler, provides improved scratch-proofness and abrasion resistance for the shaped components obtained therefrom.

This object is achieved according to the invention in that the moulding composition additionally comprises elastomer particles or elastomer particle aggregates having a particle size smaller than 100  $\mu\text{m}$  in an amount in the range of 5 % by weight to less than 20 % by weight, expressed in terms of the mass of the syrup.

The lower limit of 5 % by weight for the addition of elastomer particles or elastomer particle aggregates needs to be complied with in order to obtain a significant effect on the scratch-proofness and abrasion resistance. It is expedient to keep below the 20 % by weight limit since higher elastomer-particle contents give rise not to better, but actually to poorer results in terms of scratch-proofness and abrasion resistance.

The preferred range, in which the elastomer particles or elastomer particle aggregates are used in the



moulding composition, is in the range of 10 to 18 % by weight, expressed in terms of the mass of the syrup.

The term particle size is intended to mean the size of the individual elastomer particles or, when aggregates are present, the size of the particle aggregates.

For the present invention, it is possible to use both particles to which are present in isolation and also particle aggregates, which may remain aggregated when taken up in the syrup. Excessively large aggregates particles may be disaggregated.

The moulding composition according to the invention not only increases the abrasion resistance and scratch-proofness of the shaped component, especially when cristobalite powders are used as the inorganic filler, but also imparts even better impact strength to the shaped component, which enables a significant reduction in the wall thickness, for example of the basins of kitchen sinks.

Another advantageous effect of the moulding compositions according to the invention is that the reverse sides, i.e. the low-quality side of the shaped component, is kept relatively smooth. Furthermore, owing to faster syrup production, the moulding compositions according to the invention can be prepared more quickly overall.

If relatively coarse fillers are used in the moulding composition according to the invention, then smoother surfaces are obtained than when using the previously known formulations.

Surprisingly, the filling times for the mould cavities can furthermore be shortened, even with a reduced pressure in the filling vessel.

PMMA with a molecular weight ( $M_w$ ) in the range of from 50,000 to 250,000 may be added as a viscosity-modifying agent to the moulding composition (i.e.

firstly the syrup), in an amount of up to 20 % by weight, expressed in terms of the mass of the syrup.

The elastomer of the particles or aggregates preferably consists of partially crosslinked polymer.

5           The elastomer particles or particle aggregates preferably have particles with a core/shell structure, the core being formed by an elastomer and the shell from a matrix-compatible polymer which is essentially insoluble in the syrup. The core/shell structure pro-  
10           vides greater opportunities for variation in terms of the elastomer, since it can be selected without regard to its compatibility with the syrup.

The shell is preferably chemically bonded to the core elastomer.

15           In this case, or even if there is no chemical bonding with the core elastomer, the shell may be a thermoplastic polymer.

          The shell is preferably a partially crosslinked polymer, and also preferably the shell is swellable in  
20           the syrup of the moulding composition. In this case, the addition of elastomer particles or elastomer particle aggregates may be used at the same time as a means of modifying the viscosity of the moulding composition, and partly or fully obviates the addition of PMMA. The  
25           core elastomer of the particles preferably consists of a partially crosslinked polysiloxane, which is grafted with an acrylate monomer to form the shell.

          The structure of the core/shell particles preferably has a core proportion of from 40 to 60 % by  
30           weight, expressed in terms of the particle weight.

          The filler content in terms of inorganic filler in the moulding composition is preferably from 60 to 80 % by weight, expressed in terms of the moulding composition.

35           The moulding composition according to the invention is especially suitable for the production of sani-

008760" 7449860

tary-ware components, the term sanitary-ware components being intended to mean not only hand washbasins, toilet bowls, shower bases and bathtubs, but also dishwashing surfaces, kitchen sinks, work surfaces in the kitchen and the like.

Kitchen sinks, which are produced using the moulding composition according to the invention, can be produced with a reduced bottom thickness in the basin of the kitchen sink, equal in particular to less than 7 mm.

The increase in the impact strength with the moulding composition according to the invention may be so great that even bottom thicknesses of  $\leq 5$  mm at the bottom of the basin of the kitchen sink become possible.

Such small bottom thicknesses in the case of kitchen sinks, which can of course also be applied analogously to other shaped components, signify not only the use of less polymer material, and hence more economical production, but furthermore also signify shorter cycle times in the production of the shaped components, as well as lower weight overall, which leads to advantages for handling when these shaped components are being processed or installed.

These and further advantages of the invention will be explained in more detail below with reference to the examples.

The general production of the moulding compositions according to the invention is carried out essentially using the procedure known from the prior art, as can be found in particular in the documents, which have already been cited in the introduction, pertaining to conventional moulding compositions. For this reason, the production of the moulding compositions will be dealt with only in brief below. Starting with the methyl methacrylate monomers, the elastomer particles

or elastomer particle aggregates to be used are dispersed therein, from which a relatively viscous dispersion results. This dispersion preferably contains about 75 parts by weight of MMA and 25 parts by weight of elastomer particles or elastomer particle aggregates. The dispersion may then furthermore be diluted with MMA or alternatively with MMA/PMMA syrup, to give the desired elastomer concentration or viscosity of the syrup. The required dispersion of the elastomer particles or elastomer particle aggregates, which was described in the introduction, should be carried out with a rapidly rotating dissolver disc, in order to disaggregate excessively large aggregate particles. As mentioned above, the aggregate particles in the dispersion to be used should have a size smaller than 100  $\mu\text{m}$ . The primary particle size of the aggregates is frequently about 100 nm.

As mentioned above, preferred elastomer particles have a core/shell structure, and in the examples which follow, use will be made of an elastomer-particle material which can be obtained from the company Wacker, Burghausen, Germany and is available under the brand reference VP 445006 (hereafter referred to as the Wacker modifier).

The fillers to be used are added to the syrup containing the elastomer particles or elastomer particle aggregates in a manner which is known per se, in the form of powders, sands or grit of a large number of mineral materials known per se as inorganic fillers. Crosslinking agents, radical initiators and mould-release agents furthermore added, and the moulding composition thus obtained is then introduced into the appropriate mould cavities.

The temperature cycles for curing the moulding composition in the mould cavities are no different from the temperature cycles which have been recommended in

the prior art. In the subsequent comparative examples and examples, the following temperature cycle was used:

Before and during filling, the visible side of the mould is regulated to 60°C and its reverse side to 40°C. The moulding composition is generally at room temperature when filling.

In the mould when it has been filled, the temperature of the visible side is increased to 100°C and kept at this level for 30 min.

After the mould has been filled, its reverse-side temperature is kept regulated to 40°C for a further 10 min, and then kept at 100°C for the rest of the cycle (about 20 min).

The cured shaped components can be released from the mould at 100°C.

Wherever cristobalite powder is employed in the (comparative) examples below, quartz powder may equally well be used. The mechanical properties reported for cristobalite-filled shaped components are also obtained for those filled with quartz powder.

The properties of the shaped components obtained (kitchen sinks were produced in the examples) were then measured on the shaped components thus obtained.

For comparison with conventionally produced kitchen sinks, the properties of scratch-proofness, abrasion resistance and impact strength were examined.

The scratch-proofness was tested using a so-called "hardness and adhesion tester", model 413 from the company Erichsen, Hemer, Germany, a diamond needle with a 90° cone having been used in order to make scratches on the used side (visible side) of a sample under increasing loads of from 1 to 10 N.

The depth of these scratches was measured as Rmax using a roughness depth meter, model T 2000, with linear feed unit LV 50 from the company Hommelwerke, Villingen-Schwenningen, Germany.

In conclusion, the shaped components produced according to the invention are noteworthy in that they have a substantially improved scratch-proofness. Samples (comparative examples) which have a very high initial roughness, i.e. exhibited a very high degree of surface roughness, were excluded from the scratch-proofness testing, because the scratch depth to be found is generally much less than the roughness to be measured on the surface. In these cases, the surface roughness was merely tested, using the roughness depth meter, and indicated.

The impact strength was measured using the so-called Charpy method, based on DIN 53453. Unlike in the standard, the sample thicknesses result in this case from the thickness of the shaped-component section on which the testing is carried out. All the other conditions in the standard are followed.

The impact loading is in each case applied in such a way that there is an impact perpendicular to the visible side of the shaped component. A model 5102 instrument from the company Zwick in Ulm, Germany is used for the impact experiments.

The abrasion resistance of the visible-side surfaces of the shaped components is tested according to DIN 53754, the Taber Abrader instrument, model 5130 from the company Teledyne Taber, North Tonawanda, N. Y., USA was used as the test instrument.

#### Comparative Example 1:

1.8 kg of a normal type of PMMA in the molecular weight  $M_w$  range of from 50,000 to 200,000 was dissolved in 8.2 kg of MMA, and a mould-release agent (27 g of stearic acid from the company Merck, Germany) and a crosslinking agent (200 g of trimethylolpropane trimethacrylate from the company Degussa, Germany) were added. 17 kg of cristobalite powder (all particles < 200  $\mu\text{m}$ , silanized, with the particle size distribution

5% > 100  $\mu\text{m}$ , 42 % by weight > 32  $\mu\text{m}$ ) were then used to adjust the filler content of the moulding composition to 63 % by weight. After the addition of peroxides (35 g of Perkadox 16 and 80 g of Laurox, in each case from the company Akzo, Holland), polymerisation was carried out in suitable mould cavities, so as to form a kitchen sink. The filling time was about 45 s and the filling pressure was 3.5 bar.

The impact strength, the scratch-proofness and the Taber abrasion resistance were determined for a sample taken from the basin bottom of the shaped component, which had a thickness of 9 mm. In addition, the reverse side of the shaped component was visually assessed.

Results:

Impact strength: 4.5 kJ/m<sup>2</sup>

Scratch-proofness:

Load: (N)	10	9	8	7	6	5	4	3	2	1
Depth ( $\mu\text{m}$ )	14.9	14.4	12.3	8.0	6.9	5.6	3.0	2.0		

Abrasion resistance: 43.7 mg/100 revolutions

The reverse side was relatively smooth, and the powdered filler had not sunk.

Comparative Example 2:

0.9 kg of a normal type of PMMA in the molecular weight  $M_w$  range of from 50,000 to 200,000 was dissolved in 9.1 kg of MMA, and a mould-release agent and a crosslinking agent were added according to Comparative Example 1. The syrup thus obtained was less viscous than in Comparative Example 1. 17 kg of cristobalite powder (all particles < 200  $\mu\text{m}$ , silanized, with the particle size distribution 5% > 100  $\mu\text{m}$ , 42 % by weight > 32  $\mu\text{m}$ ) were then used to adjust the filler content of the moulding composition to 63 % by weight. After the addition of peroxides (as in Comparative Example 1), polymerisation was carried out in suitable mould cavi-

ties, so as to form a kitchen sink. The filling time was 13 s and the filling pressure was 2 bar.

The impact strength, the scratch-proofness and the Taber abrasion resistance were determined for a sample taken from the basin bottom of the shaped component, which had a thickness of 8.5 mm. In addition, the reverse side of the shaped component was visually assessed.

Results:

Impact strength: 7.5 kJ/m<sup>2</sup>

Scratch-proofness:

Load: (N)	10	9	8	7	6	5	4	3	2	1
Depth (µm)	10.4	9.4	8.8	7.4	7.5					

Abrasion resistance: 21.7 mg/100 revolutions

The reverse side was very rough. The powdered filler had sunk and the values for the scratch-proofness and the abrasion resistance were significantly improved.

Comparative Example 3:

2.0 kg of a normal type of PMMA in the molecular weight  $M_w$  range of from 50,000 to 250,000 were dissolved in 8.0 kg of MMA, and a mould-release agent (35 g of stearic acid from the company Merck, Germany) and a crosslinking agent (200 g of trimethylolpropane trimethacrylate from the company Degussa, Germany) were added. 27 kg of a sand with rounded edges in the 200 to 2000 µm particle size range (a mixture of silanized SIG types 1/8 and 2/9 from the company Dorfner in Amberg, Germany) were then added, which gave a filler proportion in the moulding composition of 73 % by weight. This moulding composition used a comparatively viscous syrup like Comparative Example 1, and a much coarser filler than Comparative Examples 1 and 2. After the addition of peroxides (40 g of Perkadox 16 and 80 g of Laurox, in each case from the company Akzo, Holland),



the moulding composition was polymerised in suitable moulds in such a way that the used side of the shaped component was turned downwards. The filling time was 70 s and the filling pressure was 5 bar.

5           The particle distribution of the shaped component was very uniform; at the same time the filler underwent slight (desired) sinking to the used side of the shaped component. The reverse side of the shaped component was very rough in parts, and after grinding, 10 the drainage area of the reverse side had small holes which impaired the leaktightness of an outlet fixture fitted to it. The thickness of the basin bottom was 10 mm.

Results:

Impact strength: 1.8 mJ/mm<sup>2</sup>,  
Surface roughness of the used side of the basin  
bottom 103.5 μm. The scratch-proofness test was not  
carried out on this sample, since it could not provide  
any meaningful data in view of the extremely high de-  
gree of surface roughness.

Example 1:

1.5 kg of silicone elastomer (type VP 445006) having an elastomer particle size (aggregates) of up to about 1 mm, from the company Wacker, Burghausen, Germany, was added to 8.5 kg of MMA and dispersed intensively in a dissolver (type Dispermat AE9) from the company VMA Getzmann, Reichshof, Germany in order to bring the aggregates to particle sizes smaller than 100  $\mu$ m. A mould-release agent and a crosslinking agent were added to the dispersion thus obtained, as in Comparative Example 1. 17 kg of cristobalite powder (all particles < 200  $\mu$ m, silanized, with the particle size distribution 5% > 100  $\mu$ m, 42 % by weight > 32  $\mu$ m) were then used to adjust the filler content of the moulding composition to 63 % by weight. After the addition of peroxides (as in Comparative Example 1), polymerisation

was carried out in suitable mould cavities, so as to form a kitchen sink. The filling time was about 30 s and it was possible reduce to the filling pressure to 1 bar.

5           The impact strength, the scratch-proofness and the Taber abrasion resistance were determined for a sample taken from the basin bottom of the shaped component, which had a thickness of 9 mm. In addition, the reverse side of the shaped component was visually as-  
10       sessed.

Results:

The following extraordinarily good impact strength was obtained: 12.8 kJ/m<sup>2</sup>

Scratch-proofness:

Load: (N)	10	9	8	7	6	5	4	3	2	1
Depth (µm)	11.1	9.9	7.3	6.0	4.9	3.7				

15           Abrasion resistance: 35 mg/100 revolutions

The filler had sunk slightly, resulting in an improved scratch-proofness and abrasion resistance, but the reverse side was nevertheless relatively smooth.

Example 2:

20           The same formulation as in Example 1 was used, but a shaped component (kitchen sink) having a smaller thickness of 5 mm at the basin bottom was produced, and the mechanical values corresponded to those in Example 1. Because of the very high impact strength, the  
25       shaped-component thickness is entirely sufficient to withstand the stresses of daily use (e.g. pan-drop test).

Example 3:

30           The results of this example are to be compared with Comparative Example 3.

1.5 kg of silicone elastomer (type VP 445006) from the company Wacker, Burghausen, Germany was added to 8.5 kg of MMA and dispersed intensively (see above).

00344.09100

00344 091300

A mould-release agent and a crosslinking agent were then added as in Comparative Example 3. 27 kg of a round sand, or a sand with rounded edges, in the 200 to 2000  $\mu\text{m}$  particle size range (a mixture of silanized SIG types 1/8 and 2/9 from the company Dorfner in Amberg, Germany) were then added, which gave a filler proportion in the moulding composition of 73 % by weight. It was possible here to omit the PMMA proportion in the formulation of Comparative Example 3.

After the addition of peroxides (as in Comparative Example 3), the moulding composition was polymerised in suitable moulds in such a way that the used side of the shaped component was turned downwards. The filling time was about 30 s and the filling pressure was 1 bar.

The particle distribution of the filler in the shaped component was very uniform; at the same time the filler underwent slight sinking to the used side of the shaped component. The reverse side of the shaped component was very rough in parts, but after grinding, the drainage area of the reverse side had no holes which could impair the leaktightness of an outlet fixture fitted to it. The thickness of the basin bottom was 10 mm.

Results:

Impact strength:  $2.7 \text{ kJ/mm}^2$

Surface roughness  $R_{\text{max}}$  of the used side of the basin bottom:  $61.6 \mu\text{m}$

Example 4:

0.3 kg of a normal type of PMMA in the molecular weight  $M_w$  range of from 50,000 to 200,000 was dissolved in 8.71 kg of MMA, and a mould-release agent and a crosslinking agent were added as in Comparative Example 1. In addition, 1.0 kg of silicone elastomer (VP 445006 from the company Wacker, Burghausen, Germany) was added in finely dispersed form. 17 kg of cristobalite powder

(all particles < 200 µm, silanized, with the particle size distribution 5% > 100 µm, 42 % by weight > 32 µm) were then used to adjust the filler content of the moulding composition to 63 % by weight. After the addition of peroxides (as in Comparative Example 1), polymerisation was carried out in suitable mould cavities, so as to form a kitchen sink. The filling time was 33 s and the vessel pressure was 1.5 bar.

The impact strength, the scratch-proofness and the Taber abrasion resistance were determined for a sample taken from the basin bottom of the shaped component, which had a thickness of 8 mm. In addition, the reverse side of the shaped component was visually assessed.

Results:

Impact strength: 10.4 kJ/m<sup>2</sup>

Scratch-proofness:

Load: (N)	10	9	8	7	6	5	4	3	2	1
Depth(µm)	13.2	11.5	9.9	8.8	6.5	3.7				

Abrasion resistance: 27.7 mg/100 revolutions

The reverse side was relatively smooth, and the filler had scarcely sunk.

Example 5:

0.7 kg of a normal type of PMMA in the molecular weight M<sub>w</sub> range of from 50,000 to 200,000 was dissolved in 8.8 kg of MMA, and a mould-release agent and a crosslinking agent were added as in Comparative Example 1. In addition, 0.5 kg of silicone elastomer (VP 445006 from the company Wacker, Burghausen, Germany) was added in finely dispersed form (aggregates < 100 µm). 17 kg of cristobalite powder (all particles < 200 µm, silanized, with the particle size distribution 5% > 100 µm, 42 % by weight > 32 µm) were then used to adjust the filler content of the moulding composition to 63 % by weight. After the addition of peroxides (as in Com-

parative Example 1), polymerisation was carried out in suitable mould cavities, so as to form a kitchen sink. The filling time was 9 s and the vessel pressure was 3 bar.

5           The impact strength, the scratch-proofness and the Taber abrasion resistance were determined for a sample taken from the basin bottom of the shaped component, which had a thickness of 8.5 mm. In addition, the reverse side of the shaped component was visually as-  
10       sessed.

Results:

Impact strength: 9.5 kJ/mm<sup>2</sup>

Scratch-proofness:

Load: (N)	10	9	8	7	6	5	4	3	2	1
Depth (µm)	10.4	10.4	9.9	7.2	5.7	3.7	2.6			

Abrasion resistance: 29.6 mg/100 revolutions

15           The reverse side was relatively smooth, and the filler had scarcely sunk.

Comparative Example 4:

2.0 kg of silicone elastomer (type VP 445006) from the company Wacker, Burghausen, Germany were added  
20       to 8.0 kg of MMA and dispersed intensively using a dissolver (type Dispermat AE9) from the company VMA Getzmann, Reichshof, Germany (aggregates < 100 µm). A mould-release agent and a crosslinking agent were, as in Comparative Example 1, added to the dispersion. 17  
25       kg of cristobalite powder (all particles < 200 µm, silanized, with the particle size distribution 5% > 100 µm, 42 % by weight > 32 µm) were then used to adjust the filler content of the moulding composition to 63 % by weight. After the addition of peroxides, polymerisa-  
30       tion was (as in Comparative Example 1) carried out in suitable mould cavities, so as to form a kitchen sink. The filling time was about 30 s and it was possible to reduce the filling pressure to 1 bar.

The impact strength, the scratch-proofness and the Taber abrasion resistance were determined for a sample taken from the basin bottom of the shaped component, which had a thickness of 8 mm. In addition, the reverse side of the shaped component was visually assessed.

Results:

Impact strength: 6.6 kJ/m<sup>2</sup>

Scratch-proofness:

Load: (N)	10	9	8	7	6	5	4	3	2	1
Depth(μm)	23.4	18.8	15.0	13.3	9.0	5.7	3.7	2.9		

10

Abrasion resistance: 49.4 mg/100 revolutions

The filler had not sunk, so improved scratch-proofness and abrasion resistance did not result; the reverse side was relatively smooth.

00344 0900

**PATENT CLAIMS**

1. Moulding composition for the production of sanitary-ware components, comprising a methyl-methacrylate-based syrup and from 50 to 85%, expressed in terms of the moulding composition, of an inorganic filler, characterised in that the moulding composition furthermore comprises elastomer particles or elastomer particle aggregates having a particle size smaller than 100  $\mu\text{m}$  in an amount in the range of 5 % by weight to < 20 % by weight, expressed in terms of the mass of the syrup.
2. Moulding composition according to Claim 1, characterised in that the syrup comprises PMMA with a molecular weight ( $M_w$ ) of from 50,000 to 250,000 in an amount of up to 20 % by weight, expressed in terms of the mass of the syrup.
3. Moulding composition according to Claim 1 or 2, characterised in that it contains a proportion of from 10 to 18 % by weight of the elastomer particles or elastomer particle aggregates, expressed in terms of the mass of the syrup.
4. Moulding composition according to one of Claims 1 to 3, characterised in that the elastomer of the particles or aggregates consists of partially crosslinked polymer.
5. Moulding composition according to one of the preceding claims, characterised in that the elastomer particles have a core/shell structure, the core being formed by an elastomer and the shell from a matrix-compatible polymer which is essentially insoluble in the syrup.
6. Moulding composition according to Claim 5, characterised in that the shell is chemically bonded to the core elastomer.

7. Moulding composition according to Claim 5 or 6, characterised in that the shell comprises a thermoplastic polymer.
8. Moulding composition according to Claim 5 or 6, characterised in that the shell comprises a partially crosslinked polymer.
9. Moulding composition according to one of Claims 5 to 8, characterised in that the shell is swellable in the syrup of the moulding composition.
10. Moulding composition according to one of Claims 5 to 9, characterised in that the shell comprises an acrylate polymer.
11. Moulding composition according to one of the preceding claims, characterised in that the core consists of a partially crosslinked polysiloxane, which is grafted with an acrylate monomer to form the shell.
12. Moulding composition according to one of Claims 5 to 11, characterised in that the proportion by weight of the core in the core/shell elastomer particles amounts to a proportion of from 40 to 60 % by weight.
13. Moulding composition according to one of the preceding claims, characterised in that the filler content is from 60 to 80 % by weight, expressed in terms of the moulding composition.
14. Sanitary-ware component, produced using a moulding composition according to one of Claims 1 to 13.
15. Sanitary-ware component in the form of a kitchen sink according to Claim 14, the bottom thickness of the kitchen sink being less than 7 mm.
16. Kitchen sink according to Claim 15, characterised in that the bottom thickness is  $\leq 5$  mm.



## ABSTRACT

In order, in the case of a moulding composition for the production of sanitary-ware components, comprising a methyl-methacrylate-based syrup and from 50 to 85%, expressed in terms of the moulding composition, of an inorganic filler, to obtain an improvement in the scratch-proofness and the abrasion resistance of the shaped components which are obtained therefrom, it is proposed that the composition furthermore comprise elastomer particles or elastomer particle aggregates having a particle size  $< 100 \mu\text{m}$  in an amount in the range of 5 % by weight to  $< 20$  % by weight, expressed in terms of the mass of the syrup.

008760" T424560